## **PRODUCT DETAILS**



## DESCRIPTION: BIODEGRADABLE STRETCH FILM ID CODE: FESTMCBIO001, FESTMNBI0001



ID CODE	DESCRIPTION	PACKAGING
FESTMCBI0001	Biodegradable stretch film 17 my machine use	Epal pallet with 15 coils
FESTMNBI0001 Biodegradable stretch transparent film 17 Cardboard-pape my manual use		Cardboard-paper box of 6 coils


Biodegradable stretch film, 17 my, High-performance PE. In case of unmanaged plastic waste, the biodegradation function will become active. Thanks to direct contact with air, light and moisture, the additive disintegrate the polymer after 2 years, transformating the plastic into biodegradable components without any microplastic.



Before two years from production, the additive is not active and the product maintains its phisical characteristics



In contact with external environment, two years after production, the additive cleaves the polymer chains.



The product is not a plastic anymore. It is completely transformed into bio-available residues: Co2, water, biomass.



Via Trento, 66/F - 20871 Vimercate (MB) - Italy Tel: +039 6082860 - Fax: 039 6082890 Website: www.simisrl.it TAC ID CODE and VAT: 07190670963 R.E.A. MB1874008 - Cap. Soc. € 100.000,00 i.v.

## **PRODUCT DETAILS**



DESCRIPTION: BIODEGRADABLE STRETCH FILM ID CODE: FESTMCBIO001, FESTMNBI0001

FILM PERFORMANCE	TEST METHOD	UNIT	MACHINE DIRECTION	TRANSVERSAL DIRECTION
TENSILE STRESS AT BREAK*	ASTM D882-10	N/mm²	> 25	>20
ELONGATION AT BREAK*	ASTM D882-10	%	> 400	> 550
TENSILE MODULUS*	ASTM D882-10	N/mm²	> 150	> 150
PUNCTURE RESISTANCE*	MSD method	J		> 0,60
ULTIMATE STRETCH*	MSD method	%		> 400
APPLICATION PERFORMANCE	MSD method		***	
CLING	MSD method	N	1,5	

The shown data are indicative values, relative to our standard production. Manupackaging reserves the right to modify them in accordance with the products development. All data refer to test conditions 23°C, 50% rel. humidity. \* Data refer to film thickness 23µm.

TOLERANCES		
FILM LENGTH	±3%	
FILM THICKNESS	±2µm	
FILM WIDTH	±3%	
INNER CORE DIAMETER	(77,0 ± 1,0) mm	



Via Trento, 66/F - 20871 Vimercate (MB) - Italy Tel: +039 6082860 - Fax: 039 6082890 Website: www.simisrl.it TAC ID CODE and VAT: 07190670963 R.E.A. MB1874008 - Cap. Soc. € 100.000,00 i.v.